

LONG BOARDS 1032

TECHNICAL DATA LAMINATE

Classification	Norm	Tarkett Value
Product type	EN 13329	Laminate floor covering
Class of use	EN 13329	32
HDF core board density	EN 323	900 kg/m ³ (± 20 kg/m ³)
Locking system		UNIFIT®

Technical characteristics

Format		Long
Dimensions		2050 x 245 mm
Complete thickness		10 mm
Bevel		4V

Performance for CE marking

Declaration of Performance	EN 14041	0132-0078-DoP-2019-06
Reaction to fire	EN 14041	Cfl-s1
Slip resistance	EN 14041	DS
Electrostatical propensity	EN 14041	< 2 kV
Thermal resistance (in m ² K/W)	EN 14041	≤ 0,15 m ² K/W
Content of Pentachlorophenol	EN 14041	< 5 ppm
Formaldehyde emission	EN 14041	E1

Technical performance

Abrasion resistance	EN 13329, annex E	AC4 (IP ≥ 4000)
Impact resistance	EN 13329, annex H	Big ball: ≥ 750 mm Small ball: ≥ 12 N
Resistance to staining	EN 438	Group 1 + 2: level 5 Group 3: level 4
Effect of furniture leg	EN 424	No damage shall be visible, when tested with foot Type 0 artefact
Effect of castor chair	EN 425 (Type W)	No change in appearance or damage
Thickness swelling	ISO 24336	≤ 18 %
Tolerance top layer	EN 13329	Length ± 0,3 mm Width ± 0,1 mm Thickness ± 0,5 mm
Light fastness	EN 13329	Grey scale ≥ level 4 (EN:20105-A02)
Static indentation by constant pressure	EN ISO 24343-1	< 0,05
Surface soundness	EN 13329, annex D	≥ 1,25 N/mm ²
Thermal resistance	EN 12667	0,08 m ² K/W

Sustainability & environment

PEFC certification	Yes
French VOC rating	A+
Emission class for building material	M1
Carb 2 compliance	Yes

Logistics information

5 planks/box	2,51 m ² /box	9,23 kg/m ²	33 boxes/pallet	82,86 m ² /pallet
--------------	--------------------------	------------------------	-----------------	------------------------------

The above information is subject to modification for the benefit of further improvement (06/2019)



EN 13329



UNIFIT
PATENTED TECHNOLOGY



Information sur le niveau d'émission de substances volatiles dans les intérieurs, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

